Data Sheet

SWL SERIES - SWL750


SWL Valve Regulated Lead-Acid Batteries (VRLA)


The SWL range is an enhanced NPL design resulting in an improved energy to density ratio, giving up to 40% extra discharge capacity. All other attributes and operational characteristics are the same, thereby maintaining the benefit of a common mechanical and electrical design for users of both products.

FEATURES

- Yuasa VRLA batteries can be used in any orientation excluding continuous use inverted.
- Standard case material is flame retardant to (UL94) HBØ.
- FR option case material is flame retardant to UL94:VØ (oxygen index 30).
- SWL batteries are manufactured in factories that comply with ISO9001:2000.
- FR option SWL's comply with BS6290 Part 4 (1997).
- SWL batteries comply with IEC 60896-21+22.

Layout







General Specifications

A second s			
Specifications	SWL750		
1) Nominal Voltage	12		
2) Nominal Wattage/Cell 10 min to 1.6V/Cell 5 min to 1.6V/Cell 3 min to 1.6V/Cell	128 196 239		
3) Weight (Approx)/Kg	9.3		
4) Energy Density (Wh/L)	88		
5) Specific Energy (Wh.kg) 10HR	36		
6) Internal Resistance (Approx)/mohm	8.5		
7) Maximum (1 min) discharge Current/A	150		
8) Maximum Short Duration (1 sec) Discharge Current in Amperes	500		
9) Operating Temperatures/°C Charge Discharge	-15 to 50 -20 to 60		
10) Percentage ChargeRetention at 20°C1 month3 months6 months	97 91 85		
11) Standard Terminal Type	l Type Zn alloy casting B		
12) Torque Nm	2.45		
13) Case Material	ABS		
Dimensions / mm			
Length +/-1 Width +/-1 Height +/-2	166 175 125		

www.yuasa-battery.co.uk


SWL


SWL SERIES - SWL750

CHARGING CHARACTERISTICS BATTERY CHARGED CHARGING CHARGE V FOR 12V E 0.25CA CONSTANT VOLTAGE CHARGING AT 20°C (68°F) (%) 140 (xCA) 0.25 120 CHARGED VOLUME 15.0 100 0.2 CHARGE VOLTAG 14.0 80 0.1 13.0 60 AFTER 100% DISCHARGE AFTER 50% DISCHARGE 0.1 40 12.0 0.05 20 11.0 CHARGING CURRENT 8 10 12 14 16 18 CHARGING TIME (HOURS)




DISCHARGE CHARACTERISTIC CURVES






CHARGING CHARACTERISTICS



Data Sheet

TEMPERATURE/LIFE CHARACTERISTIC



Charging Methods (At 20°C)

Standby use: Float charging voltage 2.275vpc

CAUTION

- Avoid short circuit.
- Do not charge in a sealed container.
- Service life and operational characteristics will be affected by temperature.
- AC Ripple reduces service life.

WARNING!

SWL (Standard) and (FR) battery types SWL1850; SWL1850-6; SWL2500, must never be installed permanently suspended by their handles; they are not designed for this purpose.



Yuasa Battery Sales (UK) Ltd Unit 22 Rassau Industrial Estate Ebbw Vale, Gwent, NP23 5SD

Tel: 08708 500312 Fax: 08708 500317 E-mail: enquiries@yuasa-sales.co.uk

Registered number 1548820

Cat. No. SWL750 February 07 E&O.E.

Distributed by		

www.yuasa-battery.co.uk