


PTFE Series 4:1

High Temperature Heat Shrink Tubing

pro-POWER



Features:

- Natural translucent PTFE 4:1 heat shrink tubing to MIL-1-23053/12 class 3, AMS3584 when heated to 327°C
- Non-flammable to ASTMD876
- Ideal for covering rollers, heaters, probes, high temperature terminals etc
- Good electrical, high temperature and chemical resistance and corrosion properties

Specifications:

Property	Test Method	Value
Physical		
Tensile psi minimum	ASTM D638	2,500 - 4,000
Elongation % minimum		225 - 450
Specific Gravity	ASTM D792	2.11 - 2.19
Low Temperature Flex	MIL-1-23053	No cracking
Coefficient of Friction	-	0.1
Flexural Modules psi × 10 ³	ASTM D798	50 - 90
Impact Strength ft.lb / in	ASTM D258	3
Heat Deflection Temperature 66 psi °F	ASTM D648	252
Electrical		
Dielectric Strength Volts / mm	ASTM D876	1,400 (35 kV / mm) min.
Volume Resistivity Ω-cm		10 ¹⁸
Dielectric Constant	ASTM D150	2.05 ±0.05
Chemical		
Water Absorption % maximum	ASTM D570	0.01
Corrosion (copper contact)	MIL-1-23053	Non-corrosive
Flammability	ASTM D876	Non-burning
Fluid Resistance	MIL-1-23053	No change in properties
Operating Temperature °C	-	-67 to +250

Specifications Table

Ordering Size	Min. Expansion Inches (mm)	Max. Recovered	Nominal Recovered Wall	Shrunk (mm)	Longitudinal Change Rate	Length (m)	Part Number
5/64	0.078 (1.981)	0.025	0.009	0.5	±10% max.	1.2	STFE4 2.0 CLR
1/8	0.125 (3.175)	0.037	0.01	0.8			STFE4 3.2 CLR

pro-POWER

PTFE Series 4:1
High Temperature Heat Shrink Tubing

pro-POWER

Ordering Size	Min. Expansion Inches (mm)	Max. Recovered	Nominal Recovered Wall	Shrunk (mm)	Longitudinal Change Rate	Length (m)	Part Number
3/16	0.187 (4.75)	0.05	0.012	1.2	±10% max.	1.2	STFE4 4.8 CLR
1/4	0.25 (6.35)	0.063		1.3			STFE4 6.4 CLR
3/8	0.375 (9.525)	0.096		2.4			STFE4 9.5 CLR
1/2	0.5 (12.7)	0.144	0.015	3.2			STFE4 12.7 CLR
3/4	0.75 (19.05)	0.224		4.8			STFE4 19.0 CLR
1	1 (25.4)	0.278		6.3			STFE4 25.4 CLR

Dimensions : Inches (Millimetres) (Unless Specified)