

# Technical Data Sheet

#### Rev. D (7/18) Page 1 of 2

# CircuitWorks<sup>®</sup> Silicone Free Heat Sink Grease

### Product# CW7270

#### **Product Description**

CircuitWorks Silicone Free Heat Sink Grease facilitates heat transfer away from electrical/electronic components and into heat sinks. This silicone-free compound shows no creep or migration over a wide temperature range. Thickened with a proprietary thermally conductive zinc oxide ceramic, the CircuitWorks Silicone Free Heat Sink Grease creates an effective heat sink interface in electrical/electronic equipment.

- Exceeds MIL-C-47113 for thermal conductivity
- Noncorrosive
- High dielectric strength
- Low migration
- Stable from -15°C to 200°C
- Nonflammable

### **Typical Applications**

CircuitWorks Silicone Free Heat Sink Grease may be used for electronics applications including:

- Effective Thermal Coupler for any Heat Sink Device
- Nonflammable Protective Coating
- High Voltage Corona Protection
- Excellent for Improving Readings on Contact Type Thermocouples
- Ideal for Silicone Sensitive Environments





# **Typical Product Data and Physical Properties**

| 51                                 | <b>y</b> 1                   |
|------------------------------------|------------------------------|
| Color:                             | White                        |
| Specific Gravity:<br>@ 25°C (77°F) | 2.4                          |
| @ 25 C (77 F)                      |                              |
| Usable Temperature Range:          | 5°F (-15°C) to 392°F (200°C) |
| Dielectric Strength:<br>v/mil      | 500                          |
| Dielectric Constant:<br>@ 100 Hz   | 4.4                          |
| Dissipative Factor:<br>@ 100 Hz    | 0.005                        |
| Volume Resistivity:<br>ohm-cm      | 1 x 10 <sup>14</sup>         |
| Arc Resistance:<br>seconds         | 120                          |
| Thermal Conductivity:              |                              |
| Cal-cm/sec-cm <sup>2</sup> -°C     | 1.7 х 10-3                   |
| BTU-in/hr-ft <sup>2</sup> -°F      | 4.92                         |
| W/m°K                              | 0.71                         |
| Shelflife                          | 5 years                      |
| RoHS Compliant                     | Yes                          |
|                                    |                              |

# CircuitWorks<sup>®</sup> Silicone Free Heat Sink Grease

# Product# CW7270

## Compatibility

CircuitWorks Silicone Free Heat Sink Grease is generally compatible with most materials used in printed circuit board fabrication.

| Material                   | Compatibility |
|----------------------------|---------------|
| Ceramic                    | Good          |
| Clean Metals               | Good          |
| Glass                      | Good          |
| Silicone Resins            | Good          |
| Painted Surfaces           | Good          |
| Plastic Surfaces           | Good          |
| Vulcanized Silicone Rubber | Good          |

### **Usage Instructions**

#### For industrial use only. Read SDS carefully prior to use.

Apply CircuitWorks Silicone Free Heat Sink Grease directly to surface or use the application tip. Remove cap from syringe and gently depress the plunger. Spread the material in a thin layer on all mounting and threaded surfaces of the device and the chassis.

**Clean-Up:** Wipe away excess material using a Chemtronics ControlWipes and thoroughly clean the surface using Chemtronics Electro-Wash PX.

# Availability

**CW7270** 8 gm / 0.28 oz Syringe

#### **Environmental Impact Data**

| ODP  | None |
|------|------|
| HCFC | None |
| VOC  | None |
| HFC  | None |
|      |      |

Ozone depletion potential (ODP) is determined in accordance with the Montreal Protocol and U.S. Clean Air Act of 1990. Hydrochlorofluorocarbons (HCFCs) are regulated under the Montreal Protocol as Class II ozone depleting substances. Volatile Organic Compound (VOC) information is calculated on a weight basis using the VOC definition of California Air Resources Board (CARB) Consumer Product Regulations, South Coast Air Quality Management District (SCAQMD) Rule 102 and the Federal definition published in 40 CFR 51.100(s). Hydrofluorocarbons (HFCs) are not currently regulated.

# **Technical and Application Assistance**

Chemtronics provides a technical hotline to answer your technical and application related questions. The toll free number is: 1-800-TECH-401.

### Note:

This information is believed to be accurate. It is intended for professional end users having the skills to evaluate and use the data properly. CHEMTRONICS does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.

Chemtronics®, Electro-Wash® and CircuitWorks® are registered trademarks of Chemtronics. All rights reserved. ControlWipes™ is a trademark of Chemtronics. All rights reserved.

