


High Density Conductive Foam

multicompPRO

**RoHS
Compliant**



Features

- Carbon impregnated conductive polyurethane foam
- Non corrosive
- Ideal for cushioning product in transit

Technical Data

Property	Test Methods	Requirement
Foam Type	N/A	Polyether polyurethane foam impregnated with rigid conductive latex
Density (kg/m ³)	BS 4443 Pt1 Method 2	33 - 55
Tensile Strength (KPa)	BS 4443 Pt1 Method 3A	70 minimum
Elongation @ Break (%)	BS 4443 Pt1 Method 3A	N/A
Loss in Tensile Strength After Heat Ageing (%)	BS 4443 Pt1 Method 3A 140°C for 16 hours	30% Max Loss
Loss in Tensile Strength After Humidity Ageing (%)	BS 4443 Pt1 Method 3A 105°C for 3 hours	30% Max Loss
Compression Set (50% Compression)	BS 4443 Pt1 Method 3A	N/A
Volume Resistivity (ohms/m)	BS 2044 Pt1 Method 3 (100V)	250 maximum

Part Number Table

Description	Part Number	Size
High Density Conductive Foam	MP004715	904 x 609 x 6mm
High Density Conductive Foam	MP004716	904 x 609 x 10mm
High Density Conductive Foam	MP004717	904 x 609 x 15mm
High Density Conductive Foam	MP004718	904 x 609 x 25mm

multicompPRO