


Conductive Foam Low Density

multicompPRO

**RoHS
Compliant**



Features

- Carbon impregnated conductive polyurethane foam
- Non corrosive
- Ideal for cushioning products in transit
- Custom sizes cut to order

Technical Data

Property	Test Methods	Result
Foam Type	N/A	Polyether polyurethane foam impregnated with rigid conductive latex
Density (kg/m ³)	ASTM D3575-84	2.8 lb/ft ³
Tensile Strength	ASTM D2575-84	19 psi
Volume Resistance	ANSI/ESD STM11.12	1 x 10 ³ - 1 x 10 ⁶ Ohms
Surface Resistance	ANSI/ESD STM 11.11	1 x 10 ³ - 1 x 10 ⁶ Ohms
Elongation @ Break (%)	BS 4443 Pt1 Method 3A	120%
Tear Strength	ASTM D3575-84	2.6 lbs
Recommended Operating Temperature Range	Internal	+180°F to -85°F
Charge Decay	FTMS 101C	< 0.03s
Product tested at both 12% and 50% RH at 23°C		

multicompPRO